

Technical data		Aquarelle Wall HFS	Aquarelle Wall/ Aquarelle Wall Borders
Classification	EN 259	Heavy duty	Heavy duty
Total thickness	EN 428	0.92 mm	0.92 mm
Wear layer thickness	EN 429	0.12 mm	0.12 mm
Total weight	EN 430	1 500 g/m ²	1 500 g/m ²
Dimensional stability	EN 434	Lengthwise: ≤ 0.60 mm Widthwise: ≤ 0.20 mm	Lengthwise: ≤ 0.60 mm Widthwise: ≤ 0.20 mm
Curl resultant to heat	EN 434	≤ 0.8 % ≤ 2 mm	≤ 2 mm
Reaction to fire	EN 13501-1	B-s2 d0 on gypsum plasterboard and on A1 or A2 substrate	C-s2 d0 on gypsum plasterboard and on A1 or A2 substrate
Seam strength (N/50 mm)	EN 684	≥ 150	
Acoustical absorption	NF EN ISO 354 α_w	0.05 (H)	0.05 (H)
Chemical resistance	EN 423	Good resistance	Good resistance
Resistance to bacteria	NF EN ISO 846	Sanitized ^(®) High fungi effect	Sanitized ^(®) High fungi effect
Colours		18 + 3 borders	27 + 20 borders
Form of delivery	EN 259	Rolls: 35 lm x 2 m Borders: 49 cm x 30-35 m	Rolls: 35 lm x 2 m Borders: 49 cm x 30-35 m